GREFENSTEIN et al., Serial No. 08/987,775

CLEAN VERSION OF AMENDMENTS

Cancel claims 32, 39, 40 and 42.

Add new claim 43 as follows:

43. (new) A laminated sheet or film comprising the following (co)extruded layers: a substrate layer comprising - based on the sum of the amounts of the following components A and B and, if used, C and/or D, which totals 100% by weight -

- 1 99% by weight component A, which is of a graft copolymer of
 - 1 99% by weight of a particulate graft base A1 comprising the following monomers:

80 - 99.99% by weight of at least one C_{1-8} -alkyl ester of acrylic acid as component A11;

0.01 -20% by weight of at least one polyfunctional crosslinking monomer as component A12;

1 - 99% by weight of a graft A2 comprising the following monomers, based on A2:

40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and

up to 60% by weight of units of acrylonitrile or methacrylonitrile as component A22;

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

61

GREFENSTEIN et al., Serial No. 08/987,775

1 - 99% by weight of component B, which is a copolymer of
40 - 100% by weight of units of styrene, a substituted styrene or a
(meth)acrylate, or mixtures thereof, as component B1, and
up to 60% by weight of acrylonitrile or methacrylonitrile as component B2;

0 - 80% by weight of component C, which is a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or mixtures thereof;

a transparent top layer of a styrene-acrylonitrile copolymer, and optionally,

between the top layer and the substrate layer, an (co)extruded interlayer of a styrene-acrylonitrile copolymer.